

## TEROSON EP 5010 TR

October 2016

### PRODUCT DESCRIPTION

<b>Technology</b>	Epoxy Resin
<b>Product type</b>	Body rework, Rebuilding of Car Body Metal Surfaces
<b>Additional Information</b>	2-component lead free solvent free

TEROSON EP 5010 TR is a solvent free, two component, high strength levelling compound based on Epoxy Resins with low density. By heating up both components the chemical reaction will accelerate. TEROSON EP 5010 TR has been specially developed for body rework and for rebuilding of car body metal surfaces to substitute traditional tin soldering. It is free of isocyanate, silicones and lead. The product has no shrinkage and is excellent for grinding. TEROSON EP 5010 TR shows no sagging and has very good modeling properties.

### APPLICATION AREAS

The material is used as a plumb free tin-solder replacement to fill and smooth damages. TEROSON EP 5010 TR works on steel and also on aluminium.

### TECHNICAL DATA

(Typical Test Results)

#### PART A

Base	Epoxy Resin
Colour	dark grey
Odour	characteristic
Density	approx. 0.8 g/cm <sup>3</sup>

#### PART B

Base	Amine
Colour	white/ light grey
Odour	of amines
Density	approx. 0.6 g/cm <sup>3</sup>

Mixing ratio A:B by volume	2:1
-------------------------------	-----

#### Mixture (PART A+B)

Colour	grey
Odour	no smell after curing

Potlife acc. to Bohlin (oscillating)	
at 20 °C	90 min(s)
at 30 °C	60 min(s)

Density (cured)	approx. 0.7 g/cm <sup>3</sup>
-----------------	-------------------------------

Water absorption	
24 hr(s) at 98 % rh and 40 °C	<0.5 % weight gain

In service temperature	-40 to 90 °C
------------------------	--------------

### PRELIMINARY STATEMENT

Prior to application it is necessary to read the **Safety**

**Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed.

### PRETREATMENT

The surfaces must be dry and free of oil, grease and dust.

For pretreatment of the application area / surface use TEROSON VR 10 / VR 20.

### APPLICATION

TEROSON EP 5010 TR is processed from universal cartridges with manual application tools (guns driven by hand, air pressure or battery). Only use cartridge pistols that are equipped with a piston rod. Insert the cartridge into a suitable application gun. Apply pressure to the cartridge to ensure a simultaneous and homogeneous flow of both components. Thereafter, clean the tip and attach the static mixer. To ensure proper mixing, discard the first approx. 5 cm of the adhesive bead. If material is left in the cartridge leave the static mixer attached. For further use of the product, simply remove the mixer and install a new one. Apply the levelling compound onto the repair area in a way that the area is sufficiently filled with excessive material. After curing excessive material is sanded back and sanding residues are removed. Thereafter clean the sanded parts with TEROSON VR 20. Further treatment (e.g. filling or painting) is executed according to the directions of the manufacturer. The use of fine filler is recommended. The material is not designed to be used on large repair areas at buses and coaches like side panels and roofs.

### CURING

TEROSON EP 5010 TR cures without additional exterior heat only by chemical reaction after mixing component A and B at room temperature. The development of reaction heat and consequently the curing time, are determined by the application temperature, layer thickness and the room temperature. Curing occurs at room temperature. For accelerated curing it is recommended to use a heat source. 60 °C object temperature for 60 minutes is recommended.

### CLEANING

Cured adhesive can only be removed mechanically. Fresh, uncured material can be removed with TEROSON VR 20.

### STORAGE

Frost sensitive	conditionally
Recommended storage temperature	15 to 25 °C
Shelf life	12 months in original packaging

**TEROSON EP 5010 TR**

October 2016

**Disclaimer****Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

**Henkel AG & Co. KGaA**

D-40191 Düsseldorf, Germany  
Phone: +49-211-797-0  
www.henkel.com

**Henkel Central Eastern Europe GmbH**

A-1030 Wien, Austria  
Phone: +43-1711-040  
www.henkel.com

**Henkel & Cie AG**

CH-4133 Pratteln, Switzerland  
Phone: +41-61-825-7000  
www.henkel.com

