




874R

Material **Butyl** LENGTH 14 in. / 350mm



CHEMICAL PERMEATION

CHEMICAL NAME	CAS NUMBER	BDT
		TTL EN374
Formaldehyde 37%	50-00-0	>480
2-Hydroxypropionic acid 85%	50-21-5	>480
Carbon Tet	56-23-5	>10
Urea (s) 35%	57-13-6	>480
Urea (s) 99%	57-13-6	>480
Urea (s) 62%	57-13-6	>480
Ethanol	64-17-5	>480
Acetic Acid 10%	64-19-7	>480
Acetic Acid 25%	64-19-7	>480
Acetic Acid 5%	64-19-7	>480
Benzoic Acid (s) 99%	65-85-0	>480
Methanol	67-56-1	>480
2-Propanol	67-63-0	>480
2-Propanone	67-64-1	>240
Chloroform	67-66-3	1-5
Salicylic acid (s) 99%	69-72-7	>480
n-Propanol	71-23-8	>480
Butanol	71-36-3	>480
Alcohol, Amyl	71-41-0	>480
Acetonitrile	75-05-8	>480
Citric Acid 50%	77-92-9	>480
Citric Acid 75%	77-92-9	>480
Citric Acid 99%	77-92-9	>480
Citric Acid 30%	77-92-9	>480
2-Butanol	78-83-1	>480
2-Butanone	78-93-3	>60

2-Propeneamide 98%	79-06-1	>480
2-Propeneamide 50%	79-06-1	>480
Alcohol, Benzyl	100-51-6	>480
1,2-Dichloroethane	107-06-2	>10
Acrylonitrile	107-13-1	>480
1,2-Ethanediol	107-21-1	>480
Methyl Propyl Ketone	107-87-9	>30
2-Pentanone, Methyl-	108-10-1	>60
2,6-Dimethyl-4-Heptanone	108-83-8	>30
Benzene, Methyl	108-88-3	6-10
Cyclohexanone	108-94-1	>480
Diethylamine	109-89-7	1-5
Hexane	110-54-3	1-5
Diethylene Glycol	111-46-6	>480
n-Octanol	111-87-5	>480
3-Methyl-1-butanol	123-51-3	>480
Butyl Acrylate	141-32-2	>30
Ethyl Acetate	141-78-6	>30
OXALIC ACID (s) 99%	144-62-7	>480
Calcium Carbonate (s) 99%	471-34-1	>480
3,8-Diamino-5-ethyl-6-phenylphenanthridinium bromide 95%	1239-45-8	>480
3,8-Diamino-5-ethyl-6-phenylphenanthridinium bromide 5%	1239-45-8	>480
3,8-Diamino-5-ethyl-6-phenylphenanthridinium bromide 1%	1239-45-8	>480
3,8-Diamino-5-ethyl-6-phenylphenanthridinium bromide 10%	1239-45-8	>480
Calcium Hydroxide (s) 95%	1305-62-0	>480
Iron Oxide (s) 99%	1309-37-1	>480
Caustic Potash 30%	1310-58-3	>480
Caustic Potash 10%	1310-58-3	>480
Caustic Potash 99%	1310-58-3	>480
Caustic Potash 45%	1310-58-3	>480
Caustic Potash 20%	1310-58-3	>480
Caustic Soda 10%	1310-73-2	>480
Caustic Soda 98%	1310-73-2	>480
Caustic Soda 20%	1310-73-2	>480
Caustic Soda 30%	1310-73-2	>480
Caustic Soda 40%	1310-73-2	>480
Caustic Soda 50%	1310-73-2	>480

dimethyl benzene	1330-20-7	6-10
Chromic Acid Solution 99%	1333-82-0	>480
Ammonia Solution 29%	1336-21-6	>480
Ammonia Solution 25%	1336-21-6	>480
Ammonia Solution 10%	1336-21-6	>480
Ammonia Solution 32%	1336-21-6	>480
Gallotannin 95%	1401-55-4	>480
Aluminum Chloride (s) 98%	7446-70-0	>480
Potassium Chloride (s) 99%	7447-40-7	>480
Hydrochloric Acid 37%	7647-01-0	>480
Hydrochloric Acid 10%	7647-01-0	>480
Muriatic Acid 20%	7647-01-0	>480
Muriatic Acid 32%	7647-01-0	>480
Sodium Chloride (s) 99%	7647-14-5	>480
Phosphoric Acid 85%	7664-38-2	>480
Phosphoric Acid 10%	7664-38-2	>480
Phosphoric Acid 50%	7664-38-2	>480
Hydrofluoric Acid 40%	7664-39-3	>480
Hydrofluoric Acid 30%	7664-39-3	>480
Hydrofluoric Acid 48%	7664-39-3	>480
Hydrofluoric Acid 10%	7664-39-3	>480
Hydrofluoric Acid 20%	7664-39-3	>480
Battery Acid 47%	7664-93-9	>480
Battery Acid 10%	7664-93-9	>480
Battery Acid 96%	7664-93-9	>240
Battery Acid 70%	7664-93-9	>480
Battery Acid 25%	7664-93-9	>480
Battery Acid 93%	7664-93-9	>240
Battery Acid 50%	7664-93-9	>480
Bleach: Sodium Hypochlorite 6%	7681-52-9	>480
Bleach: Sodium Hypochlorite 12%	7681-52-9	>480
Nitric Acid 50%	7697-37-2	>480
Nitric Acid 10%	7697-37-2	>480
Nitric Acid 35%	7697-37-2	>480
Nitric Acid 23%	7697-37-2	>480
Iron Chloride Solution 45%	7758-94-3	>480
Iron Chloride (s) 98%	7758-94-3	>480

Iron Sulfate (s) 99%	7782-63-0	>480
Hydrobromic Acid 48%	10035-10-6	>480
Boric acid (s) 99%	10043-35-3	>480
Calcium Chloride (s) 96%	10043-52-4	>480
Talc (s) 99%	14807-96-6	>480
Antimony Tributyrat 95%	53856-17-0	>480
Mineral Spirits (White Spirits Type 0)	64742-88-7	>30
Naphtha, light aromatic	64742-95-6	6-10

BDT=BREAKTHROUGH DETECTION TIME

THE LEVEL (0 TO 6) INDICATES THE TIME REQUIRED FOR DIFFERENT CHEMICALS TO PERMEATE THROUGH THE GLOVE.

TTL : TOTAL IMMERSION CHEMICAL PERMEATION BREAKTHROUGH TIME.

INT : INTERMITTENT CONTACT CHEMICAL PERMEATION BREAKTHROUGH TIME, ONE MINUTE IMMERSION OUT OF EVERY TEN, REPEATEDLY.

Warranty Limitations and Disclaimer Use

This information is provided solely as a convenience to help you evaluate our gloves in the end-user's particular application. It is the responsibility of the purchaser and/or user to determine the level of toxicity of the materials to be handled and to select the proper glove suitable for a particular application. The information provided reflects laboratory performance of gloves under carefully controlled conditions. SHOWA makes no guarantee of results and assumes no obligation or liability in connection with this information.