




NSK26

Material **Nitrile** LENGTH **26 in. / 650mm**



CHEMICAL PERMEATION

CHEMICAL NAME	CAS NUMBER	DEGRADATION RATING				BDT	
		5m	30m	60m	240m	TTL ASTM F739	INT ASTM F1383
Carbon Tet	56-23-5	G	F	F	P	>120	NT
Aminobenzene	62-53-3	G	P	NR	NR	NR	NT
Acetic Acid 84%	64-19-7	NT	NT	NT	NT	>240	>240
Methanol	67-56-1	E	E	E	E	>30	NT
2-Propanol	67-63-0	E	E	E	E	>480	>480
2-Propanone	67-64-1	G	P	P	NT	6-10	NT
Chloroform	67-66-3	NT	NT	NT	NT	1-5	NT
Dimethyl Formamide	68-12-2	G	P	NR	NR	NR	NT
n-Propanol	71-23-8	E	E	E	E	>480	>480
Butanol	71-36-3	E	E	E	E	>480	>480
Alcohol, Amyl	71-41-0	E	E	E	G	>480	>480
Benzene	71-43-2	F	P	NR	NR	NR	NT
Acetonitrile	75-05-8	E	G	G	G	6-10	NT
Chloride, Methylene	75-09-2	NR	NR	NR	NR	NR	NR
Bromoform	75-25-2	NR	NR	NR	NR	NR	NT
2-Butanone	78-93-3	F	NR	NR	NR	NR	NT
Acetate, Methyl	79-20-9	G	P	P	NR	6-10	NT
Nitrobenzene	98-95-3	F	NR	NR	NR	NR	NT
Benzaldehyde	100-52-7	F	NR	NR	NR	NR	NT
1,2-Dichloroethane	107-06-2	NT	NT	NT	NT	6-10	NT
Acrylonitrile	107-13-1	G	P	NR	NR	NR	NT
Benzene, Methyl	108-88-3	G	P	NR	NR	NR	NT
Benzene Chloride	108-90-7	P	NR	NR	NR	NR	NT
Cyclohexanone	108-94-1	G	NR	NR	NR	>30	NT
Acetate, Propyl	109-60-4	F	P	NR	NR	>10	NT
DEA	109-89-7	G	F	P	P	NR	NT

Diethylene Oxide	109-99-9	P	NR	NR	NR	NR	NT
Hexane	110-54-3	E	E	E	E	>480	>480
Cyclohexane	110-82-7	E	E	E	E	>240	NT
Butyl Acetate	123-86-4	G	F	P	NR	NR	NT
PERC	127-18-4	G	F	F	P	>60	NT
Dimethylacetamide N,N-	127-19-5	G	P	NR	NR	NR	NT
Ethyl Acetate	141-78-6	G	P	NR	NR	6-10	NT
Heptane	142-82-5	E	E	E	E	>480	>480
2,2,4-Trimethyl Pentane	540-84-1	E	E	E	E	>480	>480
Amyl Acetate	628-63-7	G	F	P	NR	NR	NT
Methyl Pyrrolidone, N-	872-50-4	NT	NT	NT	NT	>120	NT
Caustic Soda 50%	1310-73-2	E	E	E	E	>480	>480
dimethyl benzene	1330-20-7	G	P	P	NR	>10	NT
Ammonia Solution 29%	1336-21-6	E	E	E	E	>480	>480
Methyl-Tert-Butyl Ether	1634-04-4	E	E	E	G	>60	NT
Hydrochloric Acid 37%	7647-01-0	E	E	NT	E	>240	>480
Phosphoric Acid 85%	7664-38-2	E	E	E	E	>480	>480
Hydrofluoric Acid 48%	7664-39-3	NT	NT	NT	NT	>60	NT
Nitric Acid 70%	7697-37-2	NT	NT	NT	NT	>60	NT
Chlorine (Gas)	7782-50-5	NT	NT	NT	NT	>480	NT
Gasoline (unleaded)	8006-61-9	E	E	E	E	>120	NT
Kerosene	8008-20-6	E	E	E	E	>480	>480
Dry cleaning safety solvent	64475-85-0	E	E	E	E	>480	NT
Diesel Fuel	77650-28-3	E	E	E	E	>480	>480



DEGRADATION RATING

E=EXCELLENT; G=GOOD; F=FAIR; P=POOR; NR= NOT RECOMMENDED; NT=NOT TESTED

BDT=BREAKTHROUGH DETECTION TIME

THE LEVEL (0 TO 6) INDICATES THE TIME REQUIRED FOR DIFFERENT CHEMICALS TO PERMEATE THROUGH THE GLOVE.

TTL : TOTAL IMMERSION CHEMICAL PERMEATION BREAKTHROUGH TIME.

INT : INTERMITTENT CONTACT CHEMICAL PERMEATION BREAKTHROUGH TIME, ONE MINUTE IMMERSION OUT OF EVERY TEN, REPEATEDLY.

Warranty Limitations and Disclaimer Use

This information is provided solely as a convenience to help you evaluate our gloves in the end-user's particular application. It is the responsibility of the purchaser and/or user to determine the level of toxicity of the materials to be handled and to select the proper glove suitable for a particular application. The information provided reflects laboratory performance of gloves under carefully controlled conditions. SHOWA makes no guarantee of results and assumes no obligation or liability in connection with this information.