




CN751

Material **Nitrile** LENGTH 15 in. / 38mm



CHEMICAL PERMEATION

CHEMICAL NAME	CAS NUMBER	BDT
		TTL EN374
Formaldehyde 37%	50-00-0	>480
2-Hydroxypropionic acid 85%	50-21-5	>480
Nicotine 2%	54-11-5	>480
Nicotine 7%	54-11-5	>480
Nicotine 1%	54-11-5	>480
Carbon Tet	56-23-5	>480
Glycerol Solution 99%	56-81-5	>480
Glycerol Solution 70%	56-81-5	>480
Urea (s) 99%	57-13-6	>480
Urea (s) 35%	57-13-6	>480
Urea (s) 62%	57-13-6	>480
1,2-Propanediol	57-55-6	>480
Ethylenediaminetetraacetic acid (s) 98%	60-00-4	>480
Diethyl Ether	60-29-7	6-10
Aminobenzene	62-53-3	>30
Ethanol	64-17-5	>480
Acetic Acid 10%	64-19-7	>480
Acetic Acid 5%	64-19-7	>480
Acetic Acid 50%	64-19-7	>480
Acetic Acid 84%	64-19-7	>120
Acetic Acid 25%	64-19-7	>480
Acetic Acid 99%	64-19-7	>120
Benzoic Acid (s) 99%	65-85-0	>480
Benzoic Acid (s) 4%	65-85-0	>480
Methanol	67-56-1	>60
2-Propanol	67-63-0	>480

2-Propanone	67-64-1	>10
Chloroform	67-66-3	1-5
Dimethylsulfoxide (DMSO)	67-68-5	>60
Dimethyl Formamide	68-12-2	>10
Salicylic acid (s) 99%	69-72-7	>480
n-Propanol	71-23-8	>480
Butanol	71-36-3	>480
Alcohol, Amyl	71-41-0	>480
Benzene	71-43-2	>10
Chloride, Methyl (GAS)	74-87-3	NR
Iodide, Methyl	74-88-4	<1
ETHYLAMINE 70%	75-04-7	1-5
ETHYLAMINE 97%	75-04-7	NR
Acetonitrile	75-05-8	>10
Acetaldehyde	75-07-0	1-5
Chloride, Methylene	75-09-2	1-5
Carbon Disulfide	75-15-0	6-10
1,2-Epoxy Ethane (gas)	75-21-8	NR
Bromoform	75-25-2	1-5
1,1-Dichloroethene	75-35-4	<1
Acetyl Chloride	75-36-5	>10
Nitromethane	75-52-5	1-5
1,2-Epoxypropane	75-56-9	1-5
Tetramethylammonium Hydroxide 25%	75-59-2	>480
Dimethyl Sulfate	77-78-1	>10
Citric Acid 99%	77-92-9	>480
Citric Acid 30%	77-92-9	>480
Citric Acid 50%	77-92-9	>480
Citric Acid 75%	77-92-9	>480
2-Butanol	78-83-1	>480
Dichloropropane, 1,2-	78-87-5	>10
2-Butanone	78-93-3	>10
Ethylene, Trichloride	79-01-6	6-10
2-Propeneamide 98%	79-06-1	>480
2-Propeneamide 50%	79-06-1	>480
2-Propenoic Acid	79-10-7	>240
Chloroacetic Acid 70%	79-11-8	>480

Chloroacetic Acid 80%	79-11-8	>480
Acetate, Methyl	79-20-9	6-10
Methacrylic Acid 99%	79-41-4	>240
Methacrylate, Methyl	80-62-6	>10
DBP	84-74-2	>480
Vinyl Pyrrolidinone	88-12-0	>10
Toluene-2,6-diisocyanate	91-08-7	>480
Benzoyl peroxide (s) 98%	94-36-0	>480
Dichlorobenzene O-	95-50-1	>30
2-Aminotoluene	95-53-4	>60
Pseudocumene	95-63-6	>60
Butanone Oxime	96-29-7	>480
2-Ethylbutyl alcohol	97-95-0	>480
2-Furaldehyde	98-01-1	>10
Butyl Toluene, p-Tert	98-51-1	>480
(1-Methylethyl)benzene	98-82-8	>60
1-Phenylethanone	98-86-2	>10
Nitrobenzene	98-95-3	6-10
Benzene, Ethyl	100-41-4	>60
Benzene, Vinyl	100-42-5	>30
Alcohol, Benzyl	100-51-6	>30
Benzaldehyde	100-52-7	6-10
±)-2-(Chloromethyl)oxiran	106-89-8	>10
1,3-Butadiene	106-99-0	NR
1,2-Dichloroethane	107-06-2	>10
Acrylonitrile	107-13-1	6-10
1,2-Diaminoethane 99%	107-15-3	>30
2-Propen-1-ol	107-18-6	>120
1,2-Ethanediol	107-21-1	>480
Methyl Propyl Ketone	107-87-9	>10
1-methoxy-2-propanol	107-98-2	>120
Acetate, Vinyl	108-05-4	>30
2-Pentanone, Methyl-	108-10-1	>60
Acetate, Isopropyl	108-21-4	>30
PROPYLENE GLYCOL MONOMETHYL ETHER ACETATE	108-65-6	>60
2,6-Dimethyl-4-Heptanone	108-83-8	>480
Benzene, Methyl	108-88-3	>10

Benzene Chloride	108-90-7	>10
Cyclohexanol	108-93-0	>480
Cyclohexanone	108-94-1	>60
Carbolic Acid(s) 100%	108-95-2	>120
Carbolic Acid 10%	108-95-2	>120
Carbolic Acid 89%	108-95-2	>60
Dimethyl Propaneamide, N,N'-	109-55-7	>60
Acetate, Propyl	109-60-4	>30
Pentane	109-66-0	>480
1-Aminobutane	109-73-9	>10
Diethylamine	109-89-7	>30
Diethylene Oxide	109-99-9	6-10
Hexane	110-54-3	>480
Cyclohexane	110-82-7	>480
PYRIDINE	110-86-1	1-5
Diethylene oximide	110-91-8	1-5
1,5-Pentanedial 50%	111-30-8	>480
2,2-iminodiethanol	111-42-2	>240
Diethylene Glycol	111-46-6	>480
n-Octane	111-65-9	>480
2-Butoxyethanol	111-76-2	>240
n-Octanol	111-87-5	>480
Oleic Acid 98%	112-80-1	>480
1,2,4-Trichlorobenzene	120-82-1	>10
TRIETHYLAMINE	121-44-8	>120
4-Hydroxy-4-methyl-2-pentanone	123-42-2	>120
3-Methyl-1-butanol	123-51-3	>480
2,4-Pentanedione	123-54-6	1-5
Butyl Acetate	123-86-4	>60
1,4-Dioxane	123-91-1	>10
3-Methylbutyl Ethanoate	123-92-2	>10
PERC	127-18-4	>240
Dimethylacetamide N,N-	127-19-5	>10
Butyl Acrylate	141-32-2	>60
2-Aminoethanol	141-43-5	>120
Ethyl Acetate	141-78-6	>10
Heptane	142-82-5	>480

Sodium Bicarbonate, Saturated 10%	144-55-8	>480
Sodium Bicarbonate, Saturated 99%	144-55-8	>480
OXALIC ACID (s) 10%	144-62-7	>480
OXALIC ACID (s) 99%	144-62-7	>480
Sodium Lauryl Sulfate, Saturated 15%	151-21-3	>480
Sodium Lauryl Sulfate, Saturated 90%	151-21-3	>480
Potassium Bicarbonate, Saturated 99%	298-14-6	>480
Calcium Gluconate, Saturated 3%	299-28-5	>480
Calcium Gluconate, Saturated 98%	299-28-5	>480
Calcium Carbonate (s) 99%	471-34-1	>480
NINHYDRIN	485-47-2	>480
Sodium Carbonate, Saturated 99%	497-19-8	>480
Sodium Carbonate, Saturated 9%	497-19-8	>480
Trimethyl Phosphate	512-56-1	>30
Sodium Gluconate, Saturated 98%	527-07-1	>480
Sodium Gluconate, Saturated 59%	527-07-1	>480
2,2,4-Trimethyl Pentane	540-84-1	>480
3-Methyl-2-Butanone	563-80-4	>30
Potassium Carbonate, Saturated 138%	584-08-7	>480
Potassium Carbonate, Saturated 98%	584-08-7	>480
4-Methyl-meta-phenylene diisocyanate	584-84-9	>480
Butyl Ethylene	592-41-6	>480
Amyl Acetate	628-63-7	>120
Methyl Pyrrolidone, N-	872-50-4	>10
2-Bromoethyl Acetate	927-68-4	1-5
Hexamethyldisilazane	999-97-3	>480
Glyphosate Roundup 95%	1071-83-6	>480
3,8-Diamino-5-ethyl-6-phenylphenanthridinium bromide 1%	1239-45-8	>480
3,8-Diamino-5-ethyl-6-phenylphenanthridinium bromide 5%	1239-45-8	>480
Calcium Hydroxide (s) 95%	1305-62-0	>480
Calcium Oxide (s) 99%	1305-78-8	>480
Iron Oxide (s) 99%	1309-37-1	>480
Magnesium Hydroxide (s) 95%	1309-42-8	>480
Magnesium Oxide (s) 95%	1309-48-4	>480
Caustic Potash 99%	1310-58-3	>480
Caustic Potash 54%	1310-58-3	>480
Caustic Potash 45%	1310-58-3	>480

Caustic Potash 40%	1310-58-3	>480
Caustic Potash 50%	1310-58-3	>480
Zinc Oxide (s) 99%	1314-13-2	>480
Limestone, Argillaceous (s) 98%	1317-65-3	>480
Cresols	1319-77-3	>60
Divinyl Benzene	1321-74-0	>30
dimethyl benzene	1330-20-7	>60
Tricresyl Phosphate	1330-78-5	>480
Kaolin (s) 98%	1332-58-7	>480
Chromic Acid Solution 50%	1333-82-0	>10
Chromic Acid Solution 99%	1333-82-0	>480
Carbon, mesoporous (s) 99%	1333-86-4	>480
Ammonia Solution 29%	1336-21-6	>480
Ammonia Solution 25%	1336-21-6	>480
Ammonia Solution 10%	1336-21-6	>480
Ammonia Solution 32%	1336-21-6	>480
Gallotannin 95%	1401-55-4	>480
Methyl-Tert-Butyl Ether	1634-04-4	>480
Butoxypropanol	5131-66-8	>480
D-Limonene	5989-27-5	>60
Disodium Ethylenediaminetetraacetic Acid, Saturated 97%	6381-92-6	>480
Disodium Ethylenediaminetetraacetic Acid, Saturated 10%	6381-92-6	>480
Ammonium Nitrate, Saturated 98%	6484-52-2	>480
Ammonium Nitrate, Saturated 150%	6484-52-2	>480
Sodium Metasilicate, Saturated 98%	6834-92-0	>480
Sodium Metasilicate, Saturated 21%	6834-92-0	>480
Charcoal, activated (s) 99%	7440-44-0	>480
Zinc (s) 98%	7440-66-6	>480
Zinc Sulfate, Saturated 99%	7446-19-7	>480
Zinc Sulfate, Saturated 35%	7446-19-7	>480
Zinc Sulfate, Saturated 99%	7446-20-0	>480
Zinc Sulfate, Saturated 96%	7446-20-0	>480
Potassium Chloride (s) 99%	7447-40-7	>480
Potassium Chloride (s) 35%	7447-40-7	>480
Selenium Sulfide (s) 99%	7488-56-4	>480
Silicon Dioxide (s) 99%	7631-86-9	>480
Sodium Bisulfite, Saturated 95%	7631-90-5	>480

Sodium Bisulfite, Saturated 42%	7631-90-5	>480
Sodium Nitrite, Saturated 97%	7632-00-0	>480
Sodium Nitrite, Saturated 82%	7632-00-0	>480
Hydrochloric Acid 37%	7647-01-0	>480
Hydrogen Chloride (GAS) 99%	7647-01-0	NR
Muriatic Acid 20%	7647-01-0	>480
Hydrochloric Acid 10%	7647-01-0	>480
Muriatic Acid 32%	7647-01-0	>480
Sodium Chloride (s) 99%	7647-14-5	>480
Sodium Chloride (s) 36%	7647-14-5	>480
Phosphoric Acid 85%	7664-38-2	>480
Phosphoric Acid 20%	7664-38-2	>480
Phosphoric Acid 65%	7664-38-2	>480
Phosphoric Acid 25%	7664-38-2	>480
Phosphoric Acid 70%	7664-38-2	>480
Phosphoric Acid 30%	7664-38-2	>480
Phosphoric Acid 75%	7664-38-2	>480
Phosphoric Acid 10%	7664-38-2	>480
Phosphoric Acid 35%	7664-38-2	>480
Phosphoric Acid 80%	7664-38-2	>480
Phosphoric Acid 50%	7664-38-2	>480
Phosphoric Acid 40%	7664-38-2	>480
Phosphoric Acid 99%	7664-38-2	>480
Phosphoric Acid 45%	7664-38-2	>480
Phosphoric Acid 55%	7664-38-2	>480
Phosphoric Acid 15%	7664-38-2	>480
Phosphoric Acid 60%	7664-38-2	>480
Hydrofluoric Acid 30%	7664-39-3	>480
Hydrogen Fluoride(gas) 99%	7664-39-3	NR
Hydrofluoric Acid 40%	7664-39-3	>240
Hydrofluoric Acid 10%	7664-39-3	>480
Hydrofluoric Acid 48%	7664-39-3	>120
Hydrofluoric Acid 20%	7664-39-3	>480
Ammonia (Gas)	7664-41-7	NR
Battery Acid 25%	7664-93-9	>480
Battery Acid 47%	7664-93-9	>480
Battery Acid 50%	7664-93-9	>480

Battery Acid 39%	7664-93-9	>480
Battery Acid 30%	7664-93-9	>480
Battery Acid 70%	7664-93-9	>480
Battery Acid 96%	7664-93-9	>240
Battery Acid 15%	7664-93-9	>480
Battery Acid 93%	7664-93-9	>240
Battery Acid 18%	7664-93-9	>480
Battery Acid 10%	7664-93-9	>480
Sodium Fluoride, Saturated 99%	7681-49-4	>480
Sodium Fluoride, Saturated 4%	7681-49-4	>480
Bleach: Sodium Hypochlorite 6%	7681-52-9	>480
Bleach: Sodium Hypochlorite 12%	7681-52-9	>480
Sodium Metabisulfite (s) 97%	7681-57-4	>480
Nitric Acid 70%	7697-37-2	>120
Nitric Acid 50%	7697-37-2	>240
Nitric Acid 35%	7697-37-2	>480
Nitric Acid 23%	7697-37-2	>480
Nitric Acid 10%	7697-37-2	>480
Nitric Acid 65%	7697-37-2	>120
Iron (III) Chloride (s) 45%	7705-08-0	>480
Iron (III) Chloride (s) 91%	7705-08-0	>480
Iron (III) Chloride (s) 97%	7705-08-0	>480
Potassium Permanganate, Saturated 99%	7722-64-7	>480
Potassium Permanganate, Saturated 76%	7722-64-7	>480
Ammonium Phosphate, Monobasic, Saturated 98%	7722-76-1	>480
Ammonium Phosphate, Monobasic, Saturated 36%	7722-76-1	>480
Hydrogen Peroxide 3%	7722-84-1	>480
Hydrogen Peroxide 6%	7722-84-1	>480
Hydrogen Peroxide 10%	7722-84-1	>480
Hydrogen Peroxide 30%	7722-84-1	>480
Hydrogen Peroxide 50%	7722-84-1	>480
Bromine	7726-95-6	1-5
Sodium Sulfate, Saturated 99%	7757-82-6	>480
Sodium Sulfate, Saturated 28%	7757-82-6	>480
Sodium Sulfite (s) 98%	7757-83-7	>480
Sodium Sulfite (s) 27%	7757-83-7	>480
Calcium Phosphate Dibasic (s) 98%	7757-93-9	>480

Tricalcium Phosphate (s) 95%	7758-87-4	>480
Iron Chloride Solution 45%	7758-94-3	>480
Iron Chloride Solution 98%	7758-94-3	>480
Iron Chloride Solution 68%	7758-94-3	>480
Copper Sulfate, Saturated 98%	7758-98-7	>480
Copper Sulfate, Saturated 20%	7758-98-7	>480
Copper Sulfate, Saturated 98%	7758-99-8	>480
Copper Sulfate, Saturated 20%	7758-99-8	>480
Sodium Thiosulfate (s) 98%	7772-98-7	>480
Sodium Thiosulfate (s) 70%	7772-98-7	>480
Potassium Bisulfite, Saturated 95%	7773-03-7	>480
Potassium Bisulfite, Saturated 49%	7773-03-7	>480
Calcium Sulfate, Saturated 97%	7778-18-9	>480
Calcium Sulfate, Saturated 2%	7778-18-9	>480
Graphite (s) 98%	7782-42-5	>480
Chlorine (Gas)	7782-50-5	NR
Iron Sulfate (s) 29%	7782-63-0	>480
Iron Sulfate (s) 99%	7782-63-0	>480
Ammonium Phosphate, Dibasic, Saturated 69%	7783-28-0	>480
Ammonium Phosphate, Dibasic, Saturated 98%	7783-28-0	>480
Magnesium Chloride, Saturated 97%	7786-30-3	>480
Magnesium Chloride, Saturated 54%	7786-30-3	>480
Calcium Phosphate Dibasic Dihydrate (s) 98%	7789-77-7	>480
Hydroxylamine 50%	7803-49-8	>480
Gasoline (unleaded)	8006-61-9	>480
Fir Oil	8006-64-2	>480
Kerosene	8008-20-6	>480
Paraffin Oil	8012-95-1	>480
Ligroin	8032-32-4	>480
Mineral Oil - Light	8042-47-5	>480
Dry Cleaning Mineral Spirits	8052-41-3	>480
Tetrachloropropene	10436-39-2	>30
Titanium Dioxide (s) 99%	13463-67-7	>480
2-Chloro-2-Oxoethyl Acetate	13831-31-7	>120
Talc (s) 99%	14807-96-6	>480
Quartz (s) 99%	14808-60-7	>480
Iron (III) Sulfate, Saturated 25%	15244-10-7	>480

Iron (III) Sulfate, Saturated 97%	15244-10-7	>480
Calcium Magnesium Carbonate (s) 98%	16389-88-1	>480
Magnesium Carbonate (s) 95%	23389-33-5	>480
Polyethylene Glycol, Saturated 67%	25322-68-3	>480
Polyethylene Glycol, Saturated 98%	25322-68-3	>480
Antimony Tributyrat 95%	53856-17-0	>480
Dry cleaning safety solvent	64475-85-0	>480
Distillates (petroleum), hydrotreated light	64742-47-8	>480
Mineral Spirits (White Spirits Type 3)	64742-48-9	>480
Naphtha, VM & P	64742-49-0	>480
Kerosene (hydrodesulfurized)	64742-81-0	>480
Mineral Spirits (White Spirits Type 0)	64742-88-7	>480
Naphtha, light aromatic	64742-95-6	>120
Diesel Oil	68334-30-5	>480
Kerosene (Fuel Oil # 2)	68476-30-2	>480
Diesel Fuel #2	68476-34-6	>480
PETROLEUM ETHER	68476-50-6	>480
Mineral Spirits (odorless)	68551-17-7	>480

BDT=BREAKTHROUGH DETECTION TIME

THE LEVEL (0 TO 6) INDICATES THE TIME REQUIRED FOR DIFFERENT CHEMICALS TO PERMEATE THROUGH THE GLOVE.

TTL : TOTAL IMMERSION CHEMICAL PERMEATION BREAKTHROUGH TIME.

INT : INTERMITTENT CONTACT CHEMICAL PERMEATION BREAKTHROUGH TIME, ONE MINUTE IMMERSION OUT OF EVERY TEN, REPEATEDLY.

Warranty Limitations and Disclaimer Use

This information is provided solely as a convenience to help you evaluate our gloves in the end-user's particular application. It is the responsibility of the purchaser and/or user to determine the level of toxicity of the materials to be handled and to select the proper glove suitable for a particular application. The information provided reflects laboratory performance of gloves under carefully controlled conditions. SHOWA makes no guarantee of results and assumes no obligation or liability in connection with this information.