

Codan 4854 - SAE J20 R3 D2 (Up to 31.8mm) SAE J20 R4 D2 (Above 31.8mm)

Black, smooth EPDM rubber 90 degree hose for coolant and anti-freeze in cars, buses, lorries, tractors, etc

Also used in industrial applications for hot water. Part supplied with 203mm (8") legs which can be cut to suit the application.

Normally installed using hose clamps. Please contact Codan for further information. Type nr. 4854 Application: Coolant / Anti-freeze / Glycol Standard Length: 0.203 metres Working Temperature: -40°C to 125°C Inside: EPDM Colour: Black Reinforcement: Polyester Outside: EPDM Colour: Black Standards: SAE J20 R3 D2 (Up to 31.8mm) SAE J20 R4 D2 (Above 31.8mm) Std. branding: -

Inside dia. (mm)	Outside dia. (mm)	Working Pressure BAR	Burst Pressure BAR	Bend Radius (mm)	Weight (g/m)	Product code
9,5	17,5	6	17	-	100	4854010
12,7	20,7	6	17	-	105	4854013
15,9	23,9	6	17	-	145	4854016
19,1	27,1	5	14	-	150	4854019
22,3	30,0	5	14	-	200	4854022
25,4	33,4	4	12	-	300	4854025
28,6	36,6	4	12	-	320	4854028
31,8	39,8	4	12	-	350	4854031
35,0	43,0	3	9	-	400	4854035
38,1	46,1	3	8	-	410	4854038
51,0	59,0	2	7	-	520	4854051
63,0	71,0	2	6	-	680	4854063
76,0	84,0	1	4	-	850	4854076

This hose specification sheet has been prepared with great care in order to provide you with all the information you need. Written advice must be obtained from Codan Rubber before using any hose with untested media or before using in applications not covered in the product data sheet. Codan Rubber recommends regular maintenance, care and inspection of hoses before use. Hoses should be replaced if any physical damage is seen, especially to the cover of the hose or in the area around the couplings. All products must be stored in accordance with ISO 2230:2002 (Storage of vulcanised Rubber Products). The individual conditions of an application will affect the life time of each product. Therefore please ensure that resistance to chemicals and cleaning procedures in our written product information is complied with. Codan Rubber's warranty is void in the event of misuse such as excessive bending, crushing, stretching, use with incorrect media or use in environments outside the hose specification.

Please contact Codan Rubber for individual product manufacturing tolerances.



19/09/2024