


INDUSTRIAL RUBBER PRODUCTS



REACH

MECHANICAL	Standard	Value	
Rubber compound		SBR/NR	
Density	ASTM D3575	1.50 +/-0.05	g/cm3
Hardness	ASTM D2240	70 ⁰ +/-5	Shore A
Tensile strength	ISO 37	3	MPa
Elongation at break	ISO 37	≥ 200	%
Tear resistance		0	N/mm
Compression set after 24h at 70°C		0	%
TEMPERATURE			
Working temperature		-30°C - +80°C	
AGEING			
Δ Hardness		0	%
Δ Tensile		0	N/mm
Δ Elongation at break		0	%
OIL RESISTANCE			
Oil IRM 901, Δ volume after 72h at 100°C		0	%
Oil IRM 903, Δ volume after 72h at 100°C		0	%
CHEMICAL RESISTANCE			
Diluted acids and bases		Medium	
Concentrated acids and bases		Non suitable	
Ozone and UV		Medium	
Oils and hydrocarbons		Non suitable	

DIMENSIONS					
SKU	Thickness (mm)	Width (mm)	Length (m)	Inserts	Execution
4601000140	1	1400	20	0	2 sides smooth
4601500140	1,5	1400	15	0	2 sides smooth
4601510140	1,5	1400	15	1	2 sides smooth
4602000120	2	1200	10	0	2 sides smooth
4602000140	2	1400	10	0	2 sides smooth
4602010120	2	1200	10	1	2 sides smooth
4602010140	2	1400	10	1	2 sides smooth