



Data Sheet ref. 100

Properties	Standard	Unit	Ref. 100
Density	DIN 53479	g/cm ³	1,22
Shore Hardness	DIN 53505		80
Elongation at break	EN ISO 527	%	390
Water absorption	EN ISO 62	%	-0,2
Light transmission	ASTM D 1003	%	>85
Temperatur Resistance	EN 1876	°C	+50 /-15
Cold bent brittle temp	DIN 53372	°C	- 35
Sound reduction	DIN 52210	DB	> 35