



MECHANICAL	Standard	Value			
Rubber compound		EPDM/SBR			
Density	ASTM D3575	1.35 +/-0.05	g/cm3		
Hardness	ASTM D2240	65 <sup>0</sup> +/-5	Shore A		
Tensile strength	ISO 37	5	MPa		
Elongation at break	ISO 37	≥ 300	%		
Tear resistance		0	N/mm		
Compression set after 24h at 70°C		0	%		
TEMPERATURE					
Working temperature		-25°C - +100°C			
AGEING					
Δ Hardness		0	%		
Δ Tensile		0	N/mm		
Δ Elongation at break		0	%		
OIL RESISTANCE					
Oil IRM 901, Δ volume after 72h at 100°C		0	%		
Oil IRM 903, Δ volume after 72h at 100°C		0	%		
CHEMICAL RESISTANCE					
Diluted acids and bases		Medium			
Concentrated acids and basis		Medium			
Ozone and UV		Good			
Oils and hydrocarbons		Not suitable			
DIMENSIONS					
SKU	Thickness (mm)	Width (mm)	Length (m)	Inser	
5001000140	1	1400	20	0	
5001500140	1,5	1400	15	0	
5002000140	2	1400	10	0	
5003000140	3	1400	10	0	
5004000140	4	1400	10	0	
		1400	10	0	
		1400	10	0	