



# Super Dry Desiccant

## Typical Properties

Super Dry desiccants are made of Calcium Chloride and starch. Calcium Chloride is a hygroscopic salt able to attract and bind large amounts of water. At 95% RH and 50°C over a period of 30 days, the moisture absorption rate of Super Dry DS 1000 gram desiccant is over 300% of the desiccant bags net weight.

Super Dry desiccants absorb moisture and turn the resultant mix into a gel by means of an irreversible reaction, which eliminates any possibility of leakage.

## Packing Format

12 desiccant bags per carton. Each desiccant bag is airtight concealed in a high quality polypropylene bag to ensure delivery in active condition.

## Shelf Life

24 Months from date of delivery if stored in a dry warehouse with normal humidity and if packaging remains un-opened. If packaging is opened, use the desiccants as soon as possible, and re-seal immediately after use.

## Health and Safety

Calcium Chloride is an eye irritant. Calcium Chloride releases heat when adsorbing water. If a large quantity of Calcium Chloride quickly adsorbs water, the adsorbent can become hot; contact has to be avoided under these conditions. Calcium Chloride should be handled so as to avoid generation of dusty conditions at the workplace.

Under normal handling procedures, the inner and outer layer bags of the desiccant prevent direct contact of the Calcium Chloride with the workplace. Please take measures to avoid damage and destruction of the inner and outer layer linings.

For further information, please refer to our MSDS for which you please contact us through our local sales representative or by email

[www.superdryers.com](http://www.superdryers.com)



## Product Description

Brand:	Super Dry
Product Model:	DS 1000 gram
Net Weight :	1000 g
Bag Construction :	Tyvek inner lining, + PE/PP + Non-woven outer layer bag
Flat Dimensions(LxWxH) :	85.0x 17.0 x 2.0cm
Ingredients:	Calcium Chloride Starch Polyethylene
Printed Message :	RoHs REACH DMF FREE NON-TOXIC DO NOT EAT All info following the legal requirements of CLP under REACH.