



Absorption Capacity for Moler Granules

Substance	10K Sorbix Premium	20K Sorbix Plus	30K Sorbix Universal
Water	125	122	89
Oil 10/40	105	86	68
Oil T 720 15/40	110	104	66
Diesel oil	107	78	58
Hydraulic oil	105	91	66
Phosphoric acid 85 %	195	143	115
Acetic acid 32 %	132	101	74
Acetic acid 100 %	110	80	60
Hydrochloric acid 32 %	137	112	75
Sulfuric acid 95 %	192	144	122
Sulfuric acid 37 %	152	140	110
Lactic acid 90 %	155	122	88
Propylene glycol clean	124	74	73
Glycerine	154	156	99
2-propanol 70 %	97	80	62
Benzyl alcohol	127	98	79
Xylene	105	76	61
Sunflower Oil	112	95	69

Absorption capacity in % (weight/weight) tested according to CEN/TS 15366